



www.kummetal.com.tr

KUMMETAL CONVERSION TABLES

<i>Rockwell Hardness HRC</i>	<i>Brinell Hardness BHN</i>	<i>Vickers Hardness HV</i>	<i>Tensile Strength ksi</i>	<i>Tensile Strength MPa</i>
62	688	746	361	2489
61	668	720	349	2406
60	649	697	337	2324
59	631	674	326	2248
58	613	653	315	2172
57	595	633	305	2103
56	577	613	295	2034
55	559	595	286	1972
54	542	577	277	1910
53	525	560	269	1855
52	509	544	261	1800
51	494	528	253	1744
50	480	513	245	1689
49	467	498	238	1641
48	455	484	231	1593
47	444	471	224	1544
46	433	458	217	1496
45	422	446	211	1455
44	411	434	206	1420
43	401	423	201	1386
42	391	412	196	1351
41	381	402	191	1317
40	371	392	186	1282
39	361	382	181	1248
38	352	372	176	1214
37	343	363	171	1179
36	334	354	166	1145
35	325	345	162	1117
34	317	336	158	1089
33	309	327	154	1062
32	301	318	150	1034
31	293	310	146	1007
30	286	302	142	979
29	279	294	138	952
28	272	286	134	924
27	265	279	130	896
26	259	272	127	876
25	253	266	124	855
24	247	260	121	834
23	241	254	118	814
22	235	248	116	800
21	229	243	113	779
20	223	238	111	765